

Bondcoat

Description

Bondcoat is a factory mixed, highly adhesive render, designed specifically for use as a key or bonding plaster. Bondcoat is a non-acrylic plaster with high water vapour permeability (breathing activity) containing only natural minerals and additives. Primarily used as a bedding coat for fibreglass reinforcing mesh.

Bondcoat can also be used as an initial key-coat on painted surfaces and most old cladding materials when carrying out remedial work, or modernising older homes.

Features and Benefits

- Easy application and handling.
- Easy to use on vertical and overhead applications.
- Excellent abrasion resistance.
- Excellent weather and solvent resistance.
- Excellent adhesion to a variety of surfaces including AAC, brick, concrete, concrete block, clay, fibre-cement, polystyrene, rammed earth, straw bale and stone.
- A thickness of 2 – 3mm can be achieved to allow embedment of reinforcing mesh.
- Bondcoat does not decompose into hazardous by-products.
-

Limitations and Precautions

- Do not add anything other than clean water.
- Do not add liquated bonding agents.
- Do not add additional water to Bondcoat later than two hours after original mixing.
- Apply only when the temperature is between 5° and 30°.
- Do not apply if a sudden temperature drop is likely during drying/cure time.
- Do not apply in hot, dry, windy conditions.
- Plaster must be protected from rain or water in the first 24 hours.

Technical Data	
----------------	--

Bag Size	20kg
Dry Time	24 hours Cool temperatures, high film thickness or high humidity may require longer drying times.
Theoretical Coverage	4 - 5 m ² per 20kg bag
No. of coats	1 or 2 coats to embed fibreglass mesh
Flash Point	None
Thinner/Clean up	Water. Wash equipment and spills immediately with water. Ensure washing water does not enter waterways.
Theoretical VOC	1 g/kg

Surface Preparation

The surface must be dry. Remove all dirt, dust, grease, loose particles, mould or any other form of contamination from the surface. Any release agents must be completely removed.

Application

Stir the contents thoroughly before and during use.

Apply by commercial plastering machines or manual application (drill mixer only).

When embedding mesh into Bondcoat, ensure that the mesh is troweled so that it remains towards the exterior surface of the plaster, and that it is overlapped at least 100mm where it is joined.

For Best Results

- Use only high quality fiberglass mesh that is alkali resistant.
- Do not apply in direct sunlight.
- Check the finished plaster system annually for cleanliness and integrity of the applied finish coatings.

Storage Store in a dry place on dunnage or a pallet, out of direct sunlight and away from moisture for up to 6 months.

Health and Safety (Please refer to the Material Safety Data Sheet before using)

MPT Bondcoat is non-flammable, non-hazardous, non-combustible & non-explosive.

KEEP OUT OF REACH OF CHILDREN

Product Number

MPT300

V 1 - 11.15

Please ensure you are referring to the current Datasheet.

Although the information and recommendations in this document are presented in good faith and believed to be correct, APCO Coatings (NZ) Ltd makes no representation as to the completeness and accuracy thereof. In no event will APCO Coatings (NZ) Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Datasheet refers. Users of this information should rely on their own professional judgment as to the suitability of this product for a specific purpose.